

Silicone Rubber All Purpose Sealant

Physical Properties: *Silicone Rubber All Purpose Sealant*

Type:	100% Silicone Rubber	Service Temperature:	-80°F to 400°F
Color:	White, Clear, Aluminum, Bronze, Black	Odor:	Moderate
Shelf Life:	12 Months	Shrinkage:	Low
Full Cure Time:	24 Hours	Vehicle:	Solvent Based
Tack Free Time:	30 Minutes	Weight/Gallon:	8.32 lbs/gal
Application Temperature	Above 40°F		

Performance Data:

Joint Movement Capability:	Excellent	Water Resistance:	Excellent
Joint Size:	No More Than 1/2" in Width or Depth	Mildew Resistance:	Excellent
Clean-Up:	Mineral Spirits	Linear Coverage: 10 oz Cartridge	
Flexibility:	Excellent	1/8" Bead Application	96.7 ft
Painting:	Do Not Paint	1/4" Bead Application	24.2 ft

Product Description:

White Lightning® Silicone Rubber All Purpose Sealant is an interior/exterior, 100% silicone sealant.

Basic Uses:

Silicone Rubber All Purpose is commonly applied at openings around ceramic tile, tubs, showers, sinks, toilets, splashboards, countertops, windows, doors and trim. Will adhere to many surfaces including wood, glass, fiberglass, vinyl, metal and many plastics.

Surface Preparation:

Surface should be clean, dry, free from oils, dirt, old caulking, old paint or other contaminants.

Painting:

Do not paint.

Cautions:

DIRECT CONTACT WITH UNCURED SEALANT IRRITATES EYES AND SKIN! Use with adequate ventilation. Water/humidity causes curing which releases acetic acid vapors. Avoid contact with eyes and skin. Wash hands after using. Do not transfer contents to other containers for storage.

Limitations:

For best results, apply at temperatures above 40°F. Do not apply to frozen or frost covered surfaces. Not for use below grade, on aquariums or for marine use below the water line. Do not apply to granite, limestone or masonry materials.

Specifications:

Meets or exceeds performance requirements of Federal Specification TT-S-001543A Class A (COM-NBS) for silicone building sealants and TT-S-00230C Class A (COM-NBS) for one-component sealants, Canadian Specifications CAN2-19, 13-M82 and ASTM C920, Type S, Grade NS, Class 25, USE NT, G, H, O, and is NSF and USDA listed. When fully cured and washed, meets performance requirements of FDA Regulation No. 21 CFR 177.2600 subject to end use.



For more information please call or write:

White Lightning® Products · 101 Prospect Ave. NW · Cleveland, OH 44115
1-800-241-5295 Option 1 Customer Service · 1-800-241-5295 Option 2 Technical Service
www.wlcaulk.com